

SAWDUST

LOST CIRCULATION MATERIAL

SAWDUST consists of a mix of heat-treated, recycled and kiln-dried white wood with a ratio of up to 50:50. The moisture content is between 5-12%. **SAWDUST** is hammer-mill processed and screened to ¼". **SAWDUST** is primarily used to combat lost circulation in water-based muds and as an organic absorbent in the event of oil spills.

FEATURES AND BENEFITS:

- Swells, bridges and seals fractures and permeable lost circulation zones.
- Can be mixed with other LCM material to formulate LCM pills.
- Inert, does not react with drilling fluid additives.
- Is unaffected by addition of salt, acid or brine.

RECOMMENDED TREATMENT:

30-80 kg/m³

PHYSICAL PROPERTIES:

Appearance:	Beige to yellow wood fibres; pine odour
Specific Gravity:	0.4-0.6
Solubility:	Insoluble

MIXING/HANDLING:

Mix through a mixing hopper or directly into the tank; provide sufficient agitation. Refer to the SDS for specific handling requirements.

MICROTOX[®] THRESHOLD: TBD

PACKAGING: 7.3 kg bag / 75 bags/pallet